

Ball Valves for Extreme Services

Coating Type	Coating Hardness		Temperature Limit		Coating Method	Description
	HV	HRC	°F	°C		
TCC	Up to 1400	71 +/- 3	572	300	HVOF Spray	Excellent anti-wear properties under lower temperature. Suitable for media with dust or particles
CCC	900-1100	66 +/-3	977	525	HVOF Spray	Excellent resistance to cavitation erosion under high temperature and sliding wear. Suitable for high temperature, high pressure and corrosive application

